

ROKESTER DP 1970.01

TECHNICAL SPECIFICATION	PRODUCT
NUMBER	STW: KR KP/065/02
DATE	29.12.2023
CHEMICAL NAME	Polyester polyol with additives
TECHNICAL REQUIREMENTS	<p>Appearance at 25°Cviscous liquid (visually)</p> <p>Hydroxyl value, mg KOH/g180 – 200 (PN-EN ISO 2554:2001)</p> <p>Acid value, mg KOH/gmax. 1.00 (PN-EN ISO 2114:2005, solvent: acetone)</p> <p>Water, % (m/m)max. 0.10 (PN-ISO 760:2001)</p> <p>Dynamic viscosity at 25°C, mPas3000 – 8000 (PN-EN ISO 3219:2000, cone No.4, rpm 150)</p>
INFORMATIVE DATA*	Density at 25°C, g/ml ~1.23

* These informative data are not technical requirements and cannot form the basis for any claims.

USE	Aromatic polyester polyol designed for production of PUR / PIR foams.
PACKAGING	Tank wagons or tanker trucks made of stainless steel, plastic containers with a capacity of 1 m ³ , steel or plastic drums with a capacity of 200 dm ³ and other packaging as agreed with the customer.
STORAGE	Keep container tightly closed. Avoid moisture and direct sunlight. Storage temperature: 15 – 55°C. Please respect the maximum allowed temperature determined by packaging producer. Recommended usage temperature: 30 – 50°C. When using the product, remember that the viscosity increases as the temperature decreases.
SHELF LIFE	Guaranteed period of stability: 6 months from the date of manufacture. After the expiry of this period, the product can be used upon verifying the conformity of its parameters with performance requirements.

TRANSPORTATION

This product is not regulated for carriage according to ADR/RID, IMDG, ICAO/IATA.

CLASSIFICATION AND LABELLING

This technical specification is applicable only if accompanied by the Safety Data Sheet in force. Pursuant to statutory requirements, only the Safety Data Sheet includes updated safety information.

DIRECTIONS FOR HANDLING AND USAGE**WARNING:**

The temperature of supplied product is 30 – 50°C.

The information contained herein is provided in good faith, based on our state of the art knowledge and experience. We reserve the right to amend this Technical Specification as a result of technological progress and product development by the manufacturer.

This product is intended for the purposes specified herein, for industrial and professional use. To use the product for purposes other than indicated herein, please contact PCC ROKITA SA for consultation sending an e-mail to: poliestry@pcc.eu.

We cannot assume any liability for the use and application of our products, technical assistance and information provided (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations.

Therefore, it is imperative that you test our products, technical assistance and information provided to determine to your own satisfaction whether they are suitable for your needs, production, your intended uses and applications. Such analysis adopted to the conditions of the use and application should include at least application tests, technical feasibility of the suggested solutions, taking into account safety requirements, health and environmental issues.

Unless otherwise specified in writing, our products are offered under our applicable Standard Terms and Conditions of Sale available on our website. Any information, including technical assistance, is provided without warrant and can change at any time without notice. The parties explicitly agree that the Customer accepts and explicitly releases us from any liability in tort, contract or otherwise, for any loss or damage arising from the use of our products, information or technical assistance. Any declarations and recommendations other than stated herein are not valid or binding. Nothing in this document is intended to be a recommendation to use any product in violation of patent claims concerning material of intended use.