

ROKOPOL 50-B-1000

CHEMICAL NAME	Butanol, propoxylated and ethoxylated
CAS NUMBER	9038-95-3
TECHNICAL REQUIREMENTS	<p>Appearance at 25°C homogeneous liquid, colourless to yellow</p> <p>Hydroxyl number, mg KOH/g 7 – 15 (ASTM D4274-23, met. D)</p> <p>Acid value, mg KOH/g max. 0.10 (ASTM D7253-22, bromothymol blue)</p> <p>Water content, % (m/m) max. 0.08 (ASTM D4672-24)</p> <p>Hazen colour..... max. 80 (ASTM D1209-05 (2019))</p> <p>Dynamic viscosity at 25°C, mPa-s..... 2000 – 2800 (ASTM D4878-23, met. A)</p>
GENERAL DATA**	<p>Density at temp. 20°C, g/ml ~1.06</p> <p>Flash point, °C >230</p> <p>Contains BHT free antioxidants</p> <p>**These informative data are not technical requirements and cannot form the basis for any claims.</p>
APPLICATION	Rokopol 50-B-1000 is used as an additive for polyurethane materials.