

1. CHEMICAL COMPOSITION

Polyether polyol, polyoxyalkylene triol based on glycerol

2. TECHNICAL REQUIREMENTS

Appearance at 25°C	liquid free from mechanical matters
Hydroxyl value, mg KOH/g	550 – 590 (ASTM D4274-23, met. D)
Acid value, mg KOH/g	max. 0.2 (ASTM D7253-22, bromothymol blue)
Water content, % (m/m)	max. 0.2 (ASTM D4672-24)
Colour, Hazen units	max. 50 (ASTM D1209-25)
Dynamic viscosity at 25°C, mPa·s	500 – 700 (ASTM D4878-23, met. A)

3. INFORMATIVE DATA*

Molecular mass, g/mol	300
Density at temp. 20°C, g/ml	~1.05
Flash point, °C	above 200
Content of Na+ + K+, mg/l	max. 25
Contains BHT free antioxidants	

*This information data does not constitute technical requirements and cannot be the basis for a complaint.

4. APPLICATION

Rokopol G300 is used to produce polyurethane materials.

5. PACKAGING

Tank wagons or tanker trucks made of stainless steel, plastic containers with a capacity of 1 m³, steel or plastic drums with a capacity of 200 dm³ and other packaging as agreed with the customer.

6. STORAGE

Store in tightly closed containers, keep away from humidity. Avoid direct sunlight. Maximum storage temperature +40°C. Recommended use temperature 20-25°C. Viscosity increases at lower temperatures.

7. EXPIRATION DATE

Guaranteed period of stability: 12 months from the date of manufacture. After the expiry of this period, the product can be used upon verifying the conformity of its parameters with performance requirements.

8. TRANSPORT

This product is not regulated for carriage according to ADR/RID, IMDG, ICAO/IATA.

9. CLASSIFICATION AND LABELLING

This technical specification is applicable only if accompanied by the Safety Data Sheet in force. Pursuant to statutory requirements, only the Safety Data Sheet includes updated safety information.

The information contained in this document is given in good faith, based on our current knowledge and experience. The right is reserved to make changes to the Technical Specifications as a result of technological progress and product improvement by the manufacturer. The product is intended for the purposes described in this technical specification, for industrial use and by professionals. If the Buyer wishes to use the product for purposes other than those indicated herein, the Buyer should contact PCC Rokita for consultation. We are not responsible for the manner and purpose of using our products, technical assistance and information provided (whether verbal, written or in the form of production assessments), including in the form of proposed studies and recommendations. It is therefore essential to test our products, assess the level of technical support and information provided in terms of your own needs and your own production, and check that our products, technical support and information provided are applicable and can be used in the intended applications. This analysis, adapted to the conditions of use of the product, should at least take into account the conducting of application tests and the appropriateness of the proposed solutions from a technical point of view, taking into account safety requirements, health issues and environmental protection. Unless otherwise stated in writing, our products are offered in accordance with the company's standard terms and conditions of sale made available on the website. All information, including that of a technical support nature, is provided without warranty of any kind and is subject to change without notice. The parties expressly agree that the Customer accepts and expressly releases us from any liability in tort, contract or otherwise for events arising in connection with the use of our goods as well as information and support. Any statements and recommendations not included in this document are unlawful and non-binding. Nothing in this document shall be construed as a recommendation to use the products in a manner contrary to the patent claims for materials or methods of use.