

## Rokopol MH2000

<b>CHEMICAL NAME</b>	Polyether polyol, reactive polyoxyallylenetriol with higher functionality
<b>CAS NUMBER</b>	56449-05-9
<b>TECHNICAL REQUIREMENTS</b>	<p>Appearance at (25 °C)..... liquid free from suspended matter, possibility opalescent</p> <p>Hydroxyl value, mg KOH/g....28 – 31.....ASTM D4274-16, test. D</p> <p>Water content, % (m/m).....max. 0.1....ASTM D4672-12</p> <p>Acid value, mg KOH/g.....max. 0.1....ASTM D7253-16, bromothymol blue</p> <p>Viscosity at 25°C, mPas*..... 1200 –1700ASTM D4878-08, test.A</p> <p>* – parameter determined on customer's request</p>
<b>GENERAL DATA</b>	<p>Density at temp. 25°C, g/ml..... ~1.028</p> <p>Flash point, °C..... above 200</p> <p>Contains BHT free antioxidants.</p>
<b>APPLICATION</b>	Reactive high functionality polyether polyol for HR foam production.