

Rokryl SW25M

CHEMICAL NAME	Water dispersion of an aryllic-methacrylic copolymer of anionic character
TECHNICAL REQUIREMENTS	Appearance milky dispersion Dry matter, % (m/m).....24 ÷ 26 pH of product6.5 ÷ 7.5 Resistance to electrolytes 2 mol/L NH ₄ OH solution, ml.....min. 60 2 mol/L HCOOH solution, ml (*).....min. 60
GENERAL DATA	Solidification point, °Capprox. 0 Note: after thawing loses its properties Solubility in water dilutable Density at 20°C, g/mlapprox. 1.03
APPLICATION	Rokryl SW25M is used in tanning industry in the processes of coat finishing of leather.