

Rokopol FS3610

CHEMICAL NAME	Dispersion of styrene acrylonitrile copolymer in oxyalkylated triol
CAS NUMBER	57913-80-1
TECHNICAL REQUIREMENTS	Appearance at (25 °C).....white, opaque liquid Hydroxyl value, mg KOH/g...40 – 45.....ASTM D4274-16, test. D Water content, % (m/m).....max. 0.08....ASTM D4672-12 Acid value, mg KOH/g.....max. 0.1.....ASTM D7253-16), bromothymol blue Viscosity at 25°C, mPas*650 – 900...ASTM D4878-15, test. A * – parameter determined on customer's request
GENERAL DATA	Solid content, % (w/w)~ 10 Density at temp. 25°C, g/ml..... ~ 1,025 Flash point, °C..... above 200 Contains BHT free antioxidants.
APPLICATION	For production of flexible polyurethane slabstock foams exhibiting increased load bearing characteristics.