

## Rokopol MS5240

<b>CHEMICAL NAME</b>	Dispersion of styrene acrylonitrile copolymer in reactive oxyalkylated triol
<b>CAS NUMBER</b>	57913-80-1
<b>TECHNICAL REQUIREMENTS</b>	<p>Appearance at (25 °C)..... white, opaque liquid</p> <p>Hydroxyl value, mg KOH/g....20 – 23.....ASTM D4274-16, test. D</p> <p>Water content, % (m/m).....max. 0.08....ASTM D4672-12</p> <p>Acid value, mg KOH/g.....max. 0.1.....ASTM D7253-06(2011), bromothymol blue</p> <p>Viscosity at 25°C, mPas* ...3500 – 7000....ASTM D4878-15, test. A</p> <p>* – parameter determined on customer's request</p>
<b>GENERAL DATA</b>	<p>Solid content, % (w/w) * .....~ 39-41</p> <p>Density at temp. 25°C, g/ml..... ~1.04</p> <p>Flash point, °C..... above 200</p> <p>Contains BHT free antioxidants.</p>
<b>APPLICATION</b>	For production of High Resilience block and moulded polyurethane foams.