

Rokopol D2002

CHEMICAL NAME	Polyether polyol, polyoxypropylenediol
CAS NUMBER	25322-69-4
TECHNICAL REQUIREMENTS	Appearance at (25 °C).....homogeneous, clear liquid Hydroxyl value, mg KOH/g...53 – 59.....ASTM D4274-16, test. D Water content, % (m/m)..... max. 0.06....ASTM D4672-12 Acid value, mg KOH/g.....max. 0.08....ASTM D7253-16, bromothymol blue Viscosity at 25°C, mPas*.....280 – 380...ASTM D4878-15, test. A

* – parameter determined on customer's request

GENERAL DATA	Molecular weight, g/mol ~2000 Density at temp. 25°C, g/ml..... ~1.04 Flash point, °C..... above 200 Contains BHT free antioxidants.
---------------------	----------------------------------------------------------------------------------------------------------------------------------------------------

APPLICATION	For polyurethane prepolymers, hydraulic liquids and other plastics.
--------------------	---------------------------------------------------------------------