

Polymax® PA-660A

CHEMICAL NAME	Polyalkylene Glycol
INCI NAME	-
CAS NUMBER	9038-95-3
FUNCTION	Plating Additive
TECHNICAL REQUIREMENTS	Color (APHA) 60 Maximum pH (10% Aqueous).....5.5 – 7.5 Moisture, %..... 0.50 Maximum Viscosity @ 100°F..... 136 – 149 cST
GENERAL DATA	Specific Gravity @ 25°C.....1.05 Aqueous SolubilitySoluble Average Molecular Weight.....1650 Appearance @ 25°C.....Clear Liquid
APPLICATION	Polymax®PA-660A is a low foaming electroplating additive. It is recommended for use in acid zinc and electroless copper plating bath applications. The primary function of Polymax®PA-660A is grain refinement and auxiliary brightener.

Revision Date: 24.05.2016