

## Rokopol RF170

<b>CHEMICAL NAME</b>	Polyether polyol, 2,2',2''-Nitrilotriethanol, propoxylated
<b>CAS NUMBER</b>	37208-53-0
<b>TECHNICAL REQUIREMENTS</b>	Appearance at (25 °C)..... amber liquid Hydroxyl value, mg KOH/g...500 – 520...ASTM D4274-11, test. D Water content, % (m/m)..... max. 0.1.....ASTM D4672-12 Viscosity at 25°C, mPas* .....300 – 500...ASTM D4878-08, test. A  * – parameter determined on customer's request
<b>GENERAL DATA</b>	Molecular weight, g/mol..... 330 Density at temp. 25°C, g/ml..... ~1.06 Flash point, °C..... above 180 Contains BHT free antioxidants.
<b>APPLICATION</b>	Product is use as a component for production of rigid foam.