

## Rokopol MS5225

<b>CHEMICAL NAME</b>	Dispersion of styrene acrylonitrile copolymer in reactive oxyalkylated triol
<b>CAS NUMBER</b>	57913-80-1
<b>TECHNICAL REQUIREMENTS</b>	Appearance at (25 °C)..... white, opaque liquid Hydroxyl value, mg KOH/g....25 – 29.....ASTM D4274-16, test. D Water content, % (m/m).....max. 0.08....ASTM D4672-12 Acid value, mg KOH/g.....max. 0.06.....ASTM D7253-16, bromothymol blue Viscosity at 25°C, mPas* ...1800 – 2400....ASTM D4878-15, test. A  * – parameter determined on customer's request
<b>GENERAL DATA</b>	Solid content, % (w/w) * .....~ 24-26 Density at temp. 25°C, g/ml..... ~1.03 Flash point, °C..... above 200 Contains BHT free antioxidants.
<b>APPLICATION</b>	For production of High Resilience block and moulded polyurethane foams.