

Rokopol M6010

CHEMICAL NAME	Polyether polyol, glycerine-based reactive polyoxyalkylenetriol
CAS NUMBER	9082-00-2
TECHNICAL REQUIREMENTS	Appearance at (25 °C)..... homogeneous, clear liquid Hydroxyl value, mg KOH/g...27 – 29.....ASTM D4274-11, test. D Water content, % (m/m).....max. 0.1.....ASTM D4672-12 Acid value, mg KOH/g.....max. 0.1.....ASTM D7253-16, bromothymol blue Viscosity at 25°C, mPas*...1050 – 1250...ASTM D4878-08, test. A

* – parameter determined on customer's request

GENERAL DATA	Molecular weight, g/mol ~6000 Density at temp. 25°C, g/ml..... ~1.02 Flash point, °C..... above 200 Contains BHT free antioxidants.
---------------------	--

APPLICATION	For production of high resilience block and moulded polyurethane foams and other polyurethane plastics.
--------------------	---