

Polymax® PA-671

CHEMICAL NAME	Surfactant
INCI NAME	-
CAS NUMBER	Proprietary
FUNCTION	Plating Additive
TECHNICAL REQUIREMENTS	Color (Gardner)..... 5 Maximum Cloud Point, °C (1% Aqueous).....70 – 76 pH (5% Aqueous).....5.0 – 7.0 Water, %..... 12 – 15
GENERAL DATA	Appearance @ 25°C.....Clear Liquid Specific Gravity @ 25°C..... 1.1 Pounds per Gallon9.16 Average Molecular Weight..... 900 Aqueous SolubilitySoluble
APPLICATION	Polymax® PA-671 is commonly used in acid zinc plating systems to impart wetting properties and in the formulation of non-flammable brightener packages with orthochlorobenzaldehyde and benzylidene acetone. Recommended use level: 0.3 and 1.0% by wt

Revision Date: 24.05.2016