

## Rokopol RF55

<b>CHEMICAL NAME</b>	Polyether polyol, polyoxyalkylene multihydroxyls alcohol
<b>CAS NUMBER</b>	52625-13-5
<b>TECHNICAL REQUIREMENTS</b>	Appearance at (25 °C)...homogeneous, colourless or yellow liquid Hydroxyl value, mg KOH/g...475 – 515...ASTM D4274-11, test. D Water content, % (m/m).....max. 0.1.....ASTM D4672-12 Acid value, mg KOH/g.....max. 0.1.....ASTM D7253-06(2011), bromothymol blue Viscosity at 25°C, mPas*.....~9200.....ASTM D4878-08, test. A

\* – parameter determined on customer's request

<b>GENERAL DATA</b>	Molecular weight, g/mol ..... ~550 Density at temp. 25°C, g/ml..... ~1.09 Flash point, °C..... above 220 Contains BHT free antioxidants.
---------------------	---

<b>APPLICATION</b>	For the production of rigid polyurethane foams as a main polyol component and other plastics.
--------------------	---