

## Rokopol iPol

<b>CHEMICAL NAME</b>	Polymeric polyol, suspension of a polymeric material in a reactive polyether polyol
<b>CAS NUMBER</b>	9082-00-2, 66991-59-1
<b>TECHNICAL REQUIREMENTS</b>	<p>Appearance at (25 °C)..... homogeneous, white liquid</p> <p>Hydroxyl value, mg KOH/g...47 – 52.....ASTM D4274-16, test. D</p> <p>Water content, % (m/m)..... max. 0.1.....ASTM D4672-12</p> <p>Acid value, mg KOH/g.....max. 0.1.....ASTM D7253-16</p> <p>Viscosity at 25°C, mPas*...2500 – 4500...ASTM D4878-08, test.A</p> <p>* – parameter determined on customer's request</p>
<b>GENERAL DATA</b>	<p>Molecular weight, g/mol..... ~4850</p> <p>Density at temp. 25°C, g/ml..... ~1.05</p> <p>Flash point, °C..... above 220</p> <p>Contains BHT free antioxidants.</p>
<b>APPLICATION</b>	Specialty polyol for the production of high quality HR foam. It can also be used in CMHR slabstock foam, where it shows the benefit of a lower FR additives.