

ROKOPOL MH2012

CHEMICAL NAME	Dispersion of styrene acrylonitrile copolymer in oxyalkylated triol
CAS NUMBER	-
TECHNICAL REQUIREMENTS	<p>Appearance at 25°CWhite, opaque liquid</p> <p>Hydroxyl value, mg KOH/g 27 – 30 (ASTM D4274-16, met. D)</p> <p>Water content, % (m/m) max. 0.08 (ASTM D4672-12)</p> <p>Acid value, mg KOH/g max. 0.1 (ASTM D7253-16, bromothymol blue)</p> <p>Dynamic viscosity at 25°C, mPas 1500 – 2500 (ASTM D4878-15, met. A)</p> <p>Solid content, % (m/m)* ~ 12 (MB-0107)</p> <p>* - parameter determined on customer's request</p>
GENERAL DATA	<p>Density at temp. 25°C, g/ml~1.03</p> <p>Flash point, °Cabove 200</p> <p><u>Contains BHT free antioxidants</u></p>
APPLICATION	For production of High Resilience block and moulded polyurethane foams.