

Ekoproflex W-3 B

CHEMICAL NAME Prepolymer formed from diphenylmethane diisocyanate (MDI) and its isomers of long chain polyols.

TECHNICAL REQUIREMENTS

NCO content, % (m/m).....	31.5 – 32.0 (EN ISO 14896)
Density at 25°C, g/ml.....	1.19 – 1.21 (EN ISO 3675)
Dynamic viscosity at 25°C, mPas.....	15 – 90 (ASTM D487815,met.A)

APPLICATION Ekoproflex W-3 B is an isocyanate component, used for production of mattresses and cushions which have a shape memory (viscoelastic polyurethane foam). It can be processed on both low- and high pressure machines..