

# ROKOPOL MS5225

**CHEMICAL NAME** Dispersion of styrene acrylonitrile copolymer in reactive oxyalkylated triol

**CAS NUMBER** -

**TECHNICAL REQUIREMENTS**

Appearance at 25°C ..... White, opaque liquid

Hydroxyl value, mg KOH/g ..... 25 – 29  
(ASTM D4274-16, met. D)

Water content, % (m/m) ..... max. 0.08  
(ASTM D4672-12)

Acid value, mg KOH/g ..... max. 0.06  
(ASTM D7253-16, bromothymol blue)

Dynamic viscosity at 25°C, mPas ..... 1800 - 2400  
(ASTM D4878-15, met. A)

Solid content, % (m/m)\* ..... 24 – 26  
(MB-0107)

\* - parameter determined on customer's request

**GENERAL DATA**

Density at temp. 25°C, g/ml .....~1.03

Flash point, °C .....above 200

Contains BHT free antioxidants

**APPLICATION** For production of High Resilience block and moulded polyurethane foams.