

## Rokester 2416

<b>CHEMICAL NAME</b>	Polyester polyol
<b>TECHNICAL REQUIREMENTS</b>	Appearance at 25°C ..... <b>homogenous, clear liquid</b> <b>colorless to straw</b> (visually) Hydroxyl value, mg KOH/g ..... <b>225 – 245</b> (PN-EN ISO 2554) Acid value, mg KOH/g ..... <b>1,90 – 2,30</b> (PN-EN ISO 2114, solvent acetone) Water, % (m/m) ..... <b>max. 0,15</b> (PN ISO 760, solvent: methanol+chloroform 1+3(V/V)) Dynamic viscosity at 25°C, mPas ..... <b>2500 – 4500</b> (PN-EN ISO 3219, cone No.4, rpm 150)
<b>GENERAL DATA</b>	Functionality ..... <b>2</b> Density at 25°C, g/ml ..... <b>~1.23</b>
<b>APPLICATION</b>	Special polyol polyester dedicated to use in PUR / PIR foams.