

Rokester 1600

CHEMICAL NAME	Polyester polyol
TECHNICAL REQUIREMENTS	<p>Appearance at 25°Chomogenous, colorless to straw liquid (visually)</p> <p>Hydroxyl value, mg KOH/g.....150 – 170 (PN-EN ISO 2554)</p> <p>Acid value, mg KOH/g.....2.0 – 3.0 (PN-EN ISO 2114, solvent: acetone)</p> <p>Water, % (m/m)max. 0.15 (PN ISO 760, solvent: methanol + chloroform 1+3(V/V))</p> <p>Dynamic viscosity at 25°C, mPas1000 – 3000 (PN-EN ISO 3219)</p> <p>Density at 25°C, g/ml ~1.23</p>
APPLICATION	Rokester 1600 is an aromatic polyester polyol intended for use in PUR / PIR foams.