

ROKESTER 1711

CHEMICAL NAME

Polyester polyol

TECHNICAL REQUIREMENTS

Appearance at 25°C **homogenous, colorless to straw liquid**
(visually)

Hydroxyl value, mg KOH/g **185 – 195**
(PN-EN ISO 2554)

Acid value, mg KOH/g **1.00 – 1.50**
(PN-EN ISO 2114, solvent: acetone)

Water, % (m/m) **max. 0.10**
(PN ISO 760, solvent: methanol+chloroform 1+3(V/V))

Dynamic viscosity at 25°C, mPas **2500 – 3500**
(PN-EN ISO 3219, cone No.4 rpm 220)

GENERAL DATA

Density at 25°C, g/ml **~1.23**

APPLICATION

Aliphatic-aromatic polyester polyol intended for production of one-component polyurethane foams (OCF).