

ROKOPOL GS364

CHEMICAL NAME Polyether polyol based on glycerol and sucrose

CAS NUMBER -

TECHNICAL REQUIREMENTS

Appearance at 25°Chomogeneous liquid,
yellow to brown

Hydroxyl value, mg KOH/g..... 340 – 380
(ASTM D4274-11, test. D)

Water content, % (m/m)..... max.0.1
(ASTM D4672-12)

Acid value, mg KOH/g.....max 0.1
ASTM D7253-06(2011), bromothymol blue

Viscosity at 25°C, mPas*.....2 000 – 4 000
(ASTM D4878-08, test. A)

* – parameter determined on customer's request

GENERAL DATA

Density at 25°C, g/mL.....~1.08

Flash point, °C.....above 200

Contains antioxidant BHT free.

APPLICATION

Rokopol GS364 is a low viscosity poliol in general purpose rigid foam systems.