

ROFLEX 65

CHEMICAL NAME	phenol isopropylated phosphate
CAS NUMBER	68937-41-7
FUNCTION	Plasticizer
TECHNICAL REQUIREMENTS	Appearance homogenous, clear liquid Acid value, mg KOH/g..... max. 0.1 Density at 25 °C, g/cm ³ 1.15-1.20 Viscosity at 25 °C, mPa·s..... 64-75 Flash point, °C min. 228 Phenol content, % (w/w) max. 0.05
GENERAL DATA	Solubility in water at 20 °C, mg/L..... below 0.37 Other solvents..... methanol, ethanol, acetone Solidification point, °C below -20 Odour..... faint, ester Molecular weight, g/mol 370-400 Halogen free
APPLICATION	Mainly recommended in PVC formulations, as well as flame retardants in synthetic rubber industry.

Information presented herein has been given in good faith and to the best of our current knowledge and experience. The compliance of the specific properties of the supplied product with the data given herein and its fitness for the intended purpose should be checked before the product is used. The producer reserved the right to modify the information presented herein as a result of technological development and improvement of the product by producer.

PCC Rokita SA
ul. Sienkiewicza 4
56-120 Brzeg Dolny
Polska

www.pcc.rokita.pl