

ROFLEX T70L

CHEMICAL NAME	Tert-butylphenyl-phenyl phosphate Reaction mass of p-t-butylphenyldiphenyl phosphate and bis(p-t-butylphenyl) phenyl phosphate
CAS No.	-
FUNKCJA	Plasticizer
TECHNICAL REQUIREMENTS	<p>Appearance at 20-25 °C homogeneous, clear liquid</p> <p>Acid value, mg KOH/g: max. 0.1</p> <p>Density at 25°C g/cm³ 1.10 - 1.15</p> <p>Viscosity at. 25°C, mPa·s 250 - 400</p> <p>Phenol content, % (m/m) max. 0.05</p> <p>TPP contents, % (m/m) max. 2.5</p>
GENERAL INFORMATION	<p>Molecular weight, g/mol 400 - 450</p> <p>Other solvents methanol, ethanol, acetone</p> <p>Odour is faint, typical for esters</p> <p>Halogen-free</p>
ZASTOSOWANIE	Used as a softener in the processing of PVC and synthetic rubber.