

Rokester 2421

CHEMICAL NAME	Polyester polyol
TECHNICAL REQUIREMENTS	Appearance at 25°C homogenous, straw to yellow liquid (visually) Hydroxyl value, mg KOH/g 240 – 255 (PN-EN ISO 2554) Acid value, mg KOH/g 1.50 – 2.30 (PN-EN ISO 2114, solvent: acetone) Water, % (m/m) max. 0.15 (PN ISO 760, solvent: methanol + chloroform 1+3(V/V)) Dynamic viscosity at 25°C, mPas 3500 – 4000 (PN-EN ISO 3219, cone No.4, rpm 180)
GENERAL DATA	Density at 25°C, g/ml ~1.23
APPLICATION	Aromatic polyester polyol designed for the application in PUR/PIR foam.