

ROKOPOL 60-D-220

CHEMICAL NAME	Polyether polyol
CAS NUMBER	9003-11-6
TECHNICAL REQUIREMENTS	<p>Appearance at 25°C Homogeneous, colorless to yellow liquid</p> <p>Water content, % (m/m) max. 0.08 (ASTM D4672-12)</p> <p>Acid value, mg KOH/g max. 0.2 (ASTM D7253-16, bromothymol blue)</p> <p>Kinematic viscosity at 40°C, cSt 198– 242 (ASTM D445-15)</p> <p>Kinematic viscosity at 100°C, cSt 34 – 42 (ASTM D445-15)</p>
GENERAL DATA	<p>ISO VG 220</p> <p>Molecular weight, g/mol ~1900</p> <p>Viscosity index ~240</p> <p>Pour point, °C <(-35</p> <p>Flash point, °C >240</p> <p>Cloud point, °C ~83</p> <p>Functionality ~2</p> <p>Density at temp. 20°C, g/ml ~1.072</p> <p>Contains BHT free antioxidants</p>
APPLICATION	<p>Rokolub 60-D-220 is a product with high Viscosity Index, soluble in water, applied as synthetic lubricants PAG base stock, single end capped type. Belongs to the V group of base oils.</p> <p>Rokolub 60-D-...series provides superior cloud point in finished formulation particularly important when use as metal working fluids.</p> <p>Applications: Industrial gear, bearing and gas compressor lubricants. Metal working fluids and functional fluids for forming metals. It may also be applied in production of polyurethane elastomers as antifoaming agent and as plasticiser in production of rubber.</p>