

CROSSIN® 450 Open Cell Spray Foam Insulation



CHEMICAL NAME	Polyurethane system
TECHNICAL REQUIREMENTS	<p>These recommendations are based on experience in applying the spray foam with the machine Graco Reaktor H-XP3 with the gun PROBLER P2 ELITE (01 mixing chamber) and Twistork helix mixer.</p> <p>Components volumetric ratio POLY : ISO.....100 : 100 Components heating temp:..... 122 - 140°F Hoses temperature:..... 122 - 140°F Components pressure: 80 - 110 Bar (1160 - 1595 psi) Component drum temperatures: 86 – 104°F The recommended ambient temperature:50 - 95°F Recommended surface temperature should:59 - 122°F Ambient relative humidity:≤ 70% Humidity on the porous surface: to 15% Nonporous surface should be dry:(0%)</p>
GENERAL DATA	<p>Core density:..... ≥ 0.45 lb/ft³ ASTM D-1622 Fire classification Class 1 (A) Surface Burning Characteristic at 5" Flame spread index 20 Smoke development 300 ASTM E 84-15 Room corner fire test Passed NFPA 286, AC377 Thermal Resistance: 1"= 4.08 hr/sf oF/BTU Thermal Resistance 90 day: 1"=3.91 hr/sf oF/BTU ASTM C518-15 Air permeance: 0.017 L/sm² ASTM E 2178-14 Tensile strength: 3.1 psi ASTM D1623 Dimensional stability: 1 day – 1.4% 7 day – 2.0% ASTM D2126 Open cell content 98%</p>
ICC - ES approval	<p>PCC Prodex Sp. z o.o. has recieved confirmation from ICC Evaluation Service, LLC (ICC-ES), that its CROSSIN 450 Open Cell Spray Foam Insulation complies with the provisions of the:</p> <p>✓ 2018 and 2015 International Building Code® (IBC)</p>

- ✓ 2018 and 2015 International Residential Code (IRC)
- ✓ 2018 and 2018 International Energy Conservation Code (IECC)

and was evaluated to:

- ✓ 2008 ICC 700 National Green Building Standard (ICC 700-2008)

This confirmation, as evidence in ICC-ES evaluation report ESR-4003, provides guidance to code officials faced with approving the use of CROSSIN 450 Open Cell Spray Foam Insulation under these codes. The evaluation report is available online at www.ics-es.org.

APPLICATION

CROSSIN® 450 is designed for producing internal thermal and acoustic insulation by spraying. It is used for insulation of roofs, attics and various types of roofing, in wood construction, masonry, steel and skeletal systems of residential, industrial, agricultural and public buildings, hangars and media venues.

CROSSIN® 450 is a polyurethane system that must be processed using the special foaming units, equipped with a spray head.