

ROKOPOL FS3625

CHEMICAL NAME	Dispersion of styrene acrylonitrile copolymer in oxyalkylated triol
CAS NUMBER	-
TECHNICAL REQUIREMENTS	Appearance at 25°C White, opaque liquid Hydroxyl value, mg KOH/g 34 – 38 (ASTM D4274-16, met. D) Water content, % (m/m)max. 0.08 (ASTM D4672-12) Acid value, mg KOH/g max. 0.1 (ASTM D7253-16, bromothymol blue) Dynamic viscosity at 25°C, mPas 1300 – 1800 (ASTM D4878-15, met. A) Solid content, % (m/m)* ~ 25 (MB-0107) * - parameter determined on customer's request
GENERAL DATA	Density at temp. 25°C, g/ml~1.03 Flash point, °C above 200 <u>Contains BHT free antioxidants</u>
APPLICATION	For production of flexible polyurethane slabstock foams exhibiting increased load bearing characteristics.