

## ROKOPOL RF475

**CHEMICAL NAME** Polyether polyol, alkoxyated polyhydric alcohol

**CAS NUMBER** -

**TECHNICAL REQUIREMENTS**

Appearance at 25°C .....	Homogeneous liquid, yellow to brown
Hydroxyl value, mg KOH/g .....	450 – 490 (ASTM D4274-16, met. D)
Water content, % (m/m) .....	max. 0.1 (ASTM D4672-12)
Acid value, mg KOH/g .....	max. 0.1 (ASTM D7253-16, bromothymol blue)
Dynamic viscosity at 25°C, mPas* .....	11000 – 22000 (ASTM D4878-15, met.A)

\* parameter determined on customer's request

**GENERAL DATA**

Density at temp. 25°C, g/ml .....	~1.09
Flash point, °C .....	. above 200

Contains BHT free antioxidants

**APPLICATION**

Rokopol RF475 is a general purpose, high functional polyol for rigid foam systems, i.g.: in the production of spray insulation systems, sandwich panels, block foams and for other polyurethane systems.