

ROKANATE M PE 1501

CHEMICAL NAME Prepolymer base on diphenylmethane diisocyanate (MDI).

TECHNICAL REQUIREMENTS

NCO content, % (m/m).....	14.5 – 16.5 (PN-EN ISO 14896)
Density at 25°C, g/ml.....	1.11 – 1.13 (PN-EN ISO 3675)
Dynamic viscosity at 25°C, mPas.....	400 – 1200 (ASTM D4878-15, met. A)
Appearance/ colour at 25°C.....	light yellow, liquid

APPLICATION ROKANATE M PE 1501 is an isocyanate component, used for as an isocyanate component in spray polyurea coating.