

Ekopromer I24

CHEMICAL NAME	Prepolymer base on diphenylmethane diisocyanate (MDI).
TECHNICAL REQUIREMENTS	<p>NCO content, % (m/m).....24.0 – 25.0 (PN-EN ISO 14896)</p> <p>Density at 25°C, g/ml.....1.16 – 1.18 (PN-EN ISO 3675)</p> <p>Dynamic viscosity at 25°C, mPas.....250 – 550 (ASTM D4878-15, met.A)</p>
APPLICATION	Ekopromer I24 is an isocyanate component, used for production of integral polyurethane foam. It can be processed on both low- and high pressure machines.