

Rokester 7525GT

CHEMICAL NAME Aromatic polyester polyol

TECHNICAL REQUIREMENTS

Appearance at 25°C **homogenous, clear liquid**
colorless to straw
 (visually)

Hydroxyl value, mg KOH/g **170 – 190**
 (PN-EN ISO 2554)

Acid value, mg KOH/g **max. 2.30**
 (PN-EN ISO 2114, solvent acetone)

Water, % (m/m) **0.47 – 0.53**
 (PN ISO 760, solvent: methanol+chloroform 1+3(V/V))

Dynamic viscosity at 25°C, mPas **1300 – 2200**
 (PN-EN ISO 3219, cone No.2, 110 rpm)

GENERAL DATA Density at 25°C, g/ml **~1.20**

APPLICATION Aromatic polyester polyol designed for special application.