

Rokester 2116

CHEMICAL NAME	Polyester polyol
TECHNICAL REQUIREMENTS	<p>Appearance at 25°C..... homogenous, colorless to straw liquid (visually)</p> <p>Hydroxyl value, mg KOH/g.....200 – 220 (PN-EN ISO 2554)</p> <p>Acid value, mg KOH/g max. 2.50 (PN-EN ISO 2114, solvent: acetone)</p> <p>Water, % (m/m) max. 0.15 (PN ISO 760, solvent: methanol + chloroform 1+3(V/V))</p> <p>Dynamic viscosity at 25°C, mPas2000 – 3000 (PN-EN ISO 3219, cone No.2, rpm 80)</p>
GENERAL DATA	Density at 25°C, g/ml ~1.23
APPLICATION	Aromatic polyol polyester designed for special applications.