

Rokester 2430

CHEMICAL NAME	Polyester polyol
TECHNICAL REQUIREMENTS	<p>Appearance at 25°C homogenous, colorless to straw liquid (visually)</p> <p>Hydroxyl value, mg KOH/g 230 – 250 (PN-EN ISO 2554)</p> <p>Acid value, mg KOH/g 1.6 – 2.0 (PN-EN ISO 2114, solvent: acetone)</p> <p>Water, % (m/m) max. 0.15 (PN ISO 760, solvent: methanol+chloroform 1+3(V/V))</p> <p>Dynamic viscosity at 25°C, mPas 8000 – 12000 (PN-EN ISO 3219, cone No.4 rpm 80)</p>
GENERAL DATA	<p>Functionality 2</p> <p>Density at 25°C, g/ml ~1.23</p>
APPLICATION	Aromatic polyester polyol dedicated for the production of polyurethane rigid foams by the continuous lamination method.