

Rokester 3110

CHEMICAL NAME	Polyester polyol
TECHNICAL REQUIREMENTS	Appearance at 25°C homogenous, clear liquid (visually) Hydroxyl value, mg KOH/g 300 – 330 (PN-EN ISO 2554) Acid value, mg KOH/g max. 2 – 3 (PN-EN ISO 2114, solvent: acetone) Water, % (m/m) max. 0.15 (PN ISO 760, solvent: methanol + chloroform 1+3(V/V)) Dynamic viscosity at 25°C, mPas 2000 – 3000 (PN-EN ISO 3219)
GENERAL DATA	Functionality 2 Density at 25°C, g/ml ~1.24
APPLICATION	Rokester 3110 is an aromatic polyester polyol used in production of rigid polyurethane foams by laminating method.