

## ROKESTER 2402.02

**CHEMICAL NAME** Polyester polyol

**TECHNICAL REQUIREMENTS**

Appearance at 25°C ..... **homogenous, colourless to straw liquid**  
(visually)

Hydroxyl value, mg KOH/g ..... **230 – 250**  
(PN-EN ISO 2554)

Acid value, mg KOH/g ..... **0.60 – 1.00**  
(PN-EN ISO 2114, solvent: acetone)

Water, % (m/m) ..... **max. 0.15**  
(PN ISO 760, solvent: methanol + chloroform 1+3(V/V))

Dynamic viscosity at 25°C, mPas ..... **max. 5000**  
(PN-EN ISO 3219, cone No.4, rpm 160)

**GENERAL DATA** Density at 25°C, g/ml ..... **~1,23**

**APPLICATION** Rokester 2402.02 is a special polyol polyester designed for use in PUR/PIR foam.