

## Rokester 2600

CHEMICAL NAME	Polyester polyol
TECHNICAL REQUIREMENTS	<p>Appearance at 25°C ..... <b>homogenous</b> <b>clear liquid straw to olive</b> (visually)</p> <p>Hydroxyl value, mg KOH/g ..... <b>250 – 270</b> (PN-EN ISO 2554)</p> <p>Acid value, mg KOH/g ..... <b>max 1.00</b> (PN-EN ISO 2114, solvent: acetone)</p> <p>Water, % (m/m) ..... <b>max. 0.10</b> (PN ISO 760, solvent: methanol + chloroform 1+3(V/V))</p> <p>Dynamic viscosity at 25°C, mPas ..... <b>2500 – 4500</b> (PN-EN ISO 3219, cone No.4, rpm 180)</p>
GENERAL DATA	<p>Functionality ..... <b>2</b></p> <p>Density at 25°C, g/ml ..... <b>~1.24</b></p>
APPLICATION	Rokester 2600 is an aromatic polyester polyol intended for the production of one component polyurethane foams.