

ROKOPOL MS5240

CHEMICAL NAME Dispersion of styrene acrylonitrile copolymer in reactive oxyalkylated triol

CAS NUMBER -

TECHNICAL REQUIREMENTS

Appearance at 25°C	White, opaque liquid
Hydroxyl value, mg KOH/g.....	20 - 23 (ASTM D4274-16, met. D)
Water content, % (m/m).....	max. 0.08 (ASTM D4672-12)
Acid value, mg KOH/g	max. 0.1 (ASTM (ASTM D7253-16, bromothymol blue)
Dynamic Viscosity at 25°C, mPas*.....	3500 – 7000 (ASTM D4878-15, met. A)
Solid content, % (m/m)*	39 – 41 (MB- 0107)

* parameter determined on customer's request

GENERAL DATA

Density at temp. 25°C, g/ml	~1.04
Flash point, °C.....	above 200
<u>Contains BHT free antioxidants</u>	

APPLICATION For production of High Resilience block and moulded polyurethane foams.