

Rokester 7522GT

CHEMICAL NAME Aromatic polyester polyol

TECHNICAL REQUIREMENTS

Appearance at 25°C**homogenous, clear liquid**
colorless to straw
 (visually)

Hydroxyl value, mg KOH/g**190 – 215**
 (PN-EN ISO 2554)

Acid value, mg KOH/g**max. 2.00**
 (PN-EN ISO 2114, solvent acetone)

Water, % (m/m)**0.46 – 0.54**
 (PN ISO 760, solvent: methanol+chloroform 1+3(V/V))

Dynamic viscosity at 25°C, mPas**500 – 2500**
 (PN-EN ISO 3219, cone No.4, rpm 150)

GENERAL DATA Density at 25°C, g/ml **~1.20**

APPLICATION Rokester 7522GT is a special polyol polyester designed for use in PUR/PIR foam.