

ROKESTER 3016

CHEMICAL NAME	Mixture of polyols
TECHNICAL REQUIREMENTS	<p>Appearance at 25°C homogenous liquid (visually)</p> <p>Hydroxyl value, mg KOH/g 270 – 300 (PN-EN ISO 2554)</p> <p>Acid value, mg KOH/g max. 2.30 (PN-EN ISO 2114, solvent: acetone)</p> <p>Water, % (m/m) max. 0.15 (PN ISO 760, solvent: methanol + chloroform 1+3(V/V))</p> <p>Dynamic viscosity at 25°C, mPas 2800 – 5300 (PN-EN ISO 3219, cone No.4, rpm 180)</p>
GENERAL DATA	Density at 25°C, g/ml ~1,20
APPLICATION	Branched, aromatic polyester polyol for specialist application.