

Rokester 2420

CHEMICAL NAME

Polyester polyol

TECHNICAL REQUIREMENTS

Appearance at 25°C **homogenous, colorless to straw liquid**
(visually)

Hydroxyl value, mg KOH/g **230 – 250**
(PN-EN ISO 2554)

Acid value, mg KOH/g **0.60 – 1.00**
(PN-EN ISO 2114, solvent: acetone)

Water, % (m/m) **max. 0.15**
(PN ISO 760, solvent: methanol+chloroform 1+3(V/V))

Dynamic viscosity at 25°C, mPas **2000 – 4500**
(PN-EN ISO 3219, cone No.4 rpm 230)

GENERAL DATA

Functionality **2**

Density at 25°C, g/ml **~1.23**

APPLICATION

Aromatic polyester polyol dedicated for the production of polyurethane rigid foams by the continuous lamination method.