

## Rokester DP 1952.14

**CHEMICAL NAME** Aromatic polyester polyol

**TECHNICAL REQUIREMENTS**

Appearance at 25°C .....**homogenous, clear liquid**  
**colorless to straw**  
 (visually)

Hydroxyl value, mg KOH/g .....**185 – 215**  
 (PN-EN ISO 2554)

Acid value, mg KOH/g .....**2.00 – 3.00**  
 (PN-EN ISO 2114, solvent acetone)

Water, % (m/m) .....**max. 0.15**  
 (PN ISO 760, solvent: methanol+chloroform 1+3(V/V))

Dynamic viscosity at 25°C, mPas .....**max. 7000**  
 (PN-EN ISO 3219, cone No.4, 150 rpm)

**GENERAL DATA** Density at 25°C, g/ml ..... **~1.23**

**APPLICATION** Rokester DP 1952.14 - aromatic polyester polyol designed for production of PUR / PIR foams.