

ROKOPOL vTec 8888

CHEMICAL NAME	Polyether polyol
CAS NUMBER	-
TECHNICAL REQUIREMENTS	Appearance at 25°Cliquid free from suspended matter Hydroxyl value, mg KOH/g..... 120 – 140 (ASTM D4274-16, met. D) Water content, % (m/m)..... max. 0.2 (ASTM D4672-18) Acid value, mg KOH/g..... max. 0.2 (ASTM D7253-16, bromothymol blue) Dynamic Viscosity at 25°C, mPas 300 – 600 (ASTM D4878-15, met. A)
GENERAL DATA	Density at temp. 25°C, g/ml~1.02 Flash point, °C..... above 200 Contains BHT free antioxidants.
APPLICATION	Rokopol vTec 8888 is a polyol for the production of viscoelastic foam.