

ROKOPOL T

CHEMICAL NAME Polyether polyol, mixture of propoxylated triethanolamine with propoxylated o-toluenediamine

TECHNICAL REQUIREMENTS

Appearance at 25°CHomogeneous, clear brown liquid

Water content, % (m/m).....max. 0.2
(ASTM D4672-18, coulometrically or Instrument with stove)

Hydroxyl value, mg KOH/g.....400 - 480
(ASTM D4274-16, met. D)

Acid value, mg KOH/gmax. 0.1
(ASTM D7253-16, bromothymol blue)

Dynamic Viscosity at 25°C, mPas*.....600 – 2500
(ASTM D4878-15, met. A)

* parameter determined on customer's request

GENERAL DATA

Density at temp. 25°C, g/ml ~1.01

Flash point, °C above 220

Contains BHT free antioxidants

APPLICATION Rokopol T is a low viscosity polyol in general purpose polyol for rigid polyurethane foam systems.