

## ROKOPOL DE4030

**CHEMICAL NAME** Polyether polyol, reactive polyoxyalkylated polyether polyol based on propylene glycol

**CAS NUMBER** 53637-25-5; 9003-11-6

**TECHNICAL REQUIREMENTS**

Appearance at 25°C.....Liquid free from suspended matter, possibility opalescent

Hydroxyl value, mg KOH/g.....27-31  
(ASTM D4274-16, met. D)

Water content, % (m/m).....max. 0.08  
(ASTM D4672-18)

Colour, Hazen units .....max. 50  
(ASTM D1209-05(2019))

Acid value, mg KOH/g.....max. 0.1  
(ASTM D7253-06(2011), bromothymol blue)

Dynamic viscosity at 25°C, mPas\*.....1000-1800  
(ASTM D4878-15, met.A)

\* parameter determined on customer's request

**GENERAL DATA**

Molecular weight .....~ 4000

Density at temp. 25°C, g/ml.....~1.02

Content of Na<sup>+</sup> + K<sup>+</sup> , mg/l .....max. 5

Flash point, °C.....above 200

Contains BHT free antioxidants

**APPLICATION** For the production of prepolymers and other polyurethane products including molding and automotive applications.