

ROKANATE M PE 0604

CHEMICAL NAME	Prepolymer based on diphenylmethane diisocyanate (MDI)
TECHNICAL REQUIREMENTS	<p>NCO content, % (m/m).....6.5 – 7.5 (PN-EN ISO 1242)</p> <p>Density at 25°C g/ml.....1.05 – 1.07 (PN-EN ISO 3675)</p> <p>Dynamic viscosity at 25°C mPas.....500 – 800 (ASTM D4878-15, met. A)</p> <p>Appearance/ colour at 25°C.....clear, white to light yellow liquid</p>
APPLICATION	<p>ROKANATE M PE 0604 is one component polyurethane adhesive used in the production of regenerated foam blocks (rebounding foam). ROKANATE M PE 0604 does not contain organic solvents. It is cured with moisture from blow-of water vapor.</p>