

# ROKESTER 1600

<b>CHEMICAL NAME</b>	Polyester polyol
<b>TECHNICAL REQUIREMENTS</b>	<p>Appearance at 25°C .....homogenous, colorless to straw liquid (visually)</p> <p>Hydroxyl value, mg KOH/g.....150 – 170 (PN-EN ISO 2554:2001)</p> <p>Acid value, mg KOH/g.....2.0 – 3.0 (PN-EN ISO 2114:2005, solvent: acetone)</p> <p>Water, % (m/m) .....max. 0.15 (PN-ISO 760:2001)</p> <p>Dynamic viscosity at 25°C, mPas .....1000 – 3000 (PN-EN ISO 3219:2000, cone no. 2, rpm 100)</p>
<b>INFORMATION DATA*</b>	Density at 25°C, g/ml ..... ~1.23
<b>APPLICATION</b>	Rokester 1600 is an aromatic polyester polyol intended for use in PUR / PIR foams.