

EKOPRODUR S0330

CHEMICAL NAME	Polyurethane system						
TECHNICAL REQUIREMENTS	<p>These recommendations are based on experience in applying the spray foam with the machine Graco Reaktor H-XP3 with the gun PROBLER P2 ELITE (01 mixing chamber).</p> <p>Components volumetric ratio POLY : ISO 100 : 100 Components heating temp: 35 - 45°C Hoses temperature: 35 - 45°C Components pressure: 70 - 100 Bar (1015 - 1450 psi) Component drum temperatures: 15 – 30°C The recommended ambient temperature: 10 - 35°C Recommended surface temperature should: 15 - 50°C Ambient relative humidity: ≤ 70% Humidity on the porous surface: to 15% Nonporous surface should be dry: (0%)</p>						
GENERAL DATA	<p>Core density: ≥ 34 kg/m³ PN-EN 1602:2013</p> <p>Fire classification E PN-EN 13501-1+A1:2010</p> <p>Short-term water absorption by partial immersion: W_p ≤ 0,10 kg/m² PN-EN 1609:2013</p> <p>Thermal conductivity: λ_{mean,i} = 0,020 W/(m·K) λ_{90,90} = 0,021 W/(m·K)</p> <p>Declared value λ_D for the thicknesses: One diffusion-tight lining</p> <table style="margin-left: 200px;"> <tr> <td>dN < 40 mm</td> <td>0.026 W/(m·K)</td> </tr> <tr> <td>40 mm ≤ dN < 60 mm</td> <td>0.025 W/(m·K)</td> </tr> <tr> <td>dN ≥ 60 mm</td> <td>0.024 W/(m·K)</td> </tr> </table> <p style="text-align: right;">PN-EN 12667:2002</p> <p>Compressive strength at 10% relative deformation σ₁₀ ≥ 200 kPa PN-EN 826:2013-07</p> <p>Water vapor resistance coefficient: μ ≥ 60 PN-EN 12086:2013</p> <p>Dimensional stability: 70°C, 90% RH, after 48h DS(70,90)3 -20°C, after 48h DS(-20,-)3</p> <p>Adhesion of the foam perpendicularly to the surface: ≥ 100 kPa PN-EN 1607:2013</p> <p>Closed cell content ≥ 90 % PN-EN ISO 4590:2005</p>	dN < 40 mm	0.026 W/(m·K)	40 mm ≤ dN < 60 mm	0.025 W/(m·K)	dN ≥ 60 mm	0.024 W/(m·K)
dN < 40 mm	0.026 W/(m·K)						
40 mm ≤ dN < 60 mm	0.025 W/(m·K)						
dN ≥ 60 mm	0.024 W/(m·K)						

APPLICATION

EKOPRODUR S0330 is designed to perform thermal insulation by spraying, internal and external walls, ceilings, attics, tanks, pipelines and other elements with unique geometry. EKOPRODUR S0330 is processed with the help of specialized high pressure machine, equipped with a spray head. The foam's excellent insulating properties were achieved through the use of, HFO, a fourth-generation foaming agent from the hydro-fluoroolefin group with a low GWP = 1 and zero ozone depletion potential ODP = 0.