

# ROKESTER DP 1952.14

<b>CHEMICAL NAME</b>	Aromatic polyester polyol
<b>TECHNICAL REQUIREMENTS</b>	<p>Appearance at 25°C .....homogenous, clear liquid colorless to straw (visually)</p> <p>Hydroxyl value, mg KOH/g .....185 – 215 (PN-EN ISO 2554:2001)</p> <p>Acid value, mg KOH/g .....2.00 – 3.00 (PN-EN ISO 2114:2005, solvent: acetone)</p> <p>Water, % (m/m) .....max. 0.15 (PN-ISO 760:2001)</p> <p>Dynamic viscosity at 25°C, mPas .....max. 7000 (PN-EN ISO 3219:2000, cone No 4, 150 rpm)</p>
<b>GENERAL DATA*</b>	<p>Density at 25°C, g/ml ..... ~1.23</p> <p>* These informative data are not technical requirements and cannot form the basis for any claims..</p>
<b>APPLICATION</b>	Aromatic polyester polyol designed for production of PUR / PIR foams.