

ROKESTER 2402.01

CHEMICAL NAME	Polyester polyol
TECHNICAL REQUIREMENTS	Appearance at 25°Chomogenous, colourless to straw liquid (visually) Hydroxyl value, mg KOH/g230 – 250 (PN-EN ISO 2554:2001) Acid value, mg KOH/g1.50 – 2.50 (PN-EN ISO 2114:2005, solvent: acetone) Water, % (m/m)max. 0.15 (PN ISO 760:2001) Dynamic viscosity at 25°C, mPasmax. 5000 (PN-EN ISO 3219:2000, cone No.4, rpm 160)
INFORMATIVE DATA*	Density at 25°C, g/ml ~1,23 Flash point, °C 179 * These informative data are not technical requirements and cannot form the basis for any claims.
APPLICATION	A specialist polyol designed for the production of PUR/PIR foams.